

Specification

Ref: KR50-04

Summary: Silicone TC 15 onto brickwork

JOB DESCRIPTION

SPECIFICATION CLAUSE: M20 - PLASTERED / RENDERED / ROUGHCAST COATINGS

To be read with Preliminaries/General Conditions.

160 Proprietary cement gauged render

- **Substrate:** Clay, concrete and calcium silicate brickwork.
- **Manufacturer:** Kilwaughter Chemical Co. Ltd.
9 Starbog Rd, Larne, Co. Antrim, N. Ireland, BT40 2TJ
Tel: 028 2826 0766 Fax: 028 2826 0136
www.K-Rend.co.uk
- **Primer:** K Rend R7 Acrylic diluted with water 1:4, applied by brush or roller and the K Rend HP12 Base applied whilst the primer is still wet or tacky.
- **Undercoat:** K Rend HP12 Base
Thickness: 10 mm. Rule to line and level. Leave with a float finish. Allow to cure for a minimum of 14 days.
- **Primer:** K Rend Primer TC, applied by brush or roller. Allow to cure for a minimum of 24 hours prior to application of final finish coat.
Colour: Selected by Specifier (colour co-ordinated with finish coat).
- **Final finish coat:** K Rend Silicone TC 15
Colour: Selected by Specifier.
Finish: Fine textured.
- **Total thickness:** 12 mm (finished)

K Rend HP12 Base and K Rend Silicone TC 15 should be applied strictly in accordance with the manufacturer's instructions and specifications and the relevant sections of BS 5262:1991 and BS EN 13914-1:2005. Further guidance is available in the British Board of Agrément, Certificate No. 97/3428 and the National Standards Authority of Ireland (NSAI), Agrément Certificate No. 06/0248.

IF THESE INSTRUCTIONS ARE NOT FOLLOWED CLOSELY, A SATISFACTORY FINISH MAY NOT BE ACHIEVED AND KILWAUGHTER CHEMICAL CO LTD WILL ACCEPT NO RESPONSIBILITY.

This specification is valid for 6 months from date of issue. Thereafter details should be re-checked with Kilwaughter Chemical Co. Ltd.

DESIGN CONSIDERATIONS

New construction to be rendered should be designed and constructed in accordance with the relevant recommendations of BS 5628:2003, BS5262:1991 and BS EN 13914-1:2005.

Render should only be applied to mature, stable surfaces. New walls to be rendered should be left as long as possible to minimise substrate movement.

In order to achieve the best finish K Bead PVC Angle, Stop, Bellcast, Drip and Expansion Beads should be used. The K Bead range is available with K Rend products from Kilwaughter Chemical Co. Ltd.

Render must not be applied to horizontal or sloping surfaces. Rendering should not be continued over movement joints, damp-proof courses, weep holes or air vents.

An adequate flashing must always be provided to prevent water penetrating behind the render.

Suitably designed overhangs and flashings should be provided to prevent water washing onto the façade. A generous overhang or eave should be designed and all sills and copings should have sufficient drips, including mortar joints at coping. Gutters and down-pipes must also be designed to keep water off the façade.

In order to minimise damage to the rendering, consideration should be given to installing fixings for rainwater, soil and vent pipes before rendering commences. The pipes themselves should be fitted after rendering is completed. Fixings should be made of stainless steel to minimise the risk of corrosion.

Independent scaffolding should be used to avoid the need to repair plug holes. Sufficient height and clearance should be allowed to enable satisfactory completion of the rendered finish.

Some construction materials may be susceptible to alkali attack. Fittings and adjacent surfaces that are likely to be damaged during rendering should be protected.

BACKGROUND AND PREPARATION

Clay, concrete or calcium silicate brickwork.

The background should be assessed to ensure that it is suitable to receive the K Rend render system. It should also be checked for line and level to decide if the render can be applied in a uniform thickness or if dubbing out is required. Following suitable preparation of the background K Rend Standard UF Base should be used for any dubbing out requirement.

All necessary repairs must be carried out before application. All damage to substrate from salt attack, corrosion or salts must be carefully prepared. Damaged bricks must be replaced and any holes or insufficiently filled joints repaired.

It is recommended that K Rend alkali resistant reinforcing mesh is used in areas likely to suffer from stress cracking. This can be done by applying K Rend HP12 Base, bedding mesh into it whilst it is still wet and leaving the HP12 Base with a light scratch prior to setting. K Rend alkali resistant reinforcing mesh is available with all K Rend products from Kilwaughter Chemical Co. Ltd.

The surface must be clean and free from any loose or friable material including paint, oil, soot, lichens and dust. If there is any algae present it should be treated with a proprietary fungicidal wash or surface biocide (i.e. Algae Clean) and then pressure washed to remove any residue.

The product should not be applied to frost bound walls.

Apply suction control as necessary; it may be necessary to damp down walls prior to applying the product to control suction. Rendering should not be applied to walls which have been subject to rain over several hours.

PRODUCT

K Rend R7 Acrylic primer (a modified Styrene-Acrylic emulsion used to improve the adhesion of K-Rend renders to “difficult” substrates).

K Rend HP12 Base (a high polymer cost effective enhanced performance basecoat).

K Rend Primer TC (synthetic resin primer for K Rend thin coat finishes).

Colour as selected by the Specifier (colour co-ordinated with finish coat).

K Rend Silicone TC 15 (thin coat synthetic resin plaster).

Colour as selected by the Specifier.

Samples are provided on request for colour indication only.

It is recommended that a test panel (ideally 2 m²) be produced for inspection by the customer (client, architect etc). Work should not commence until the customer is satisfied with the appearance of the product. Applicators should be familiar with product water requirement, handling characteristics, setting and hardening times. These may vary according to background temperature and humidity. The test panel should be prepared well in advance of work commencing.

K Rend products are manufactured from natural products and slight shade variations may occur.

K Rend bagged products are delivered in sealed 25 kg bags on pallets. Each complete pallet contains 70 bags and weighs 1.75 tonne.

K Rend paste products are delivered in 25 kg tubs on pallets. Each complete pallet contains 30 tubs and weighs 0.75 tonne.

Storage

Product sacks, even when protected by hoods, are only shower proof, and should be further protected to prevent damp causing caking of the product.

Product tubs should be protected from frost and direct sunlight.

The shelf life is 1 year from date of manufacture if stored off the ground in dry conditions, protected from frost and sunlight, in original unopened packaging.

It is important to note that all K Rend products are non-returnable.

Health and Safety

A Material Safety Data Sheet is available from the manufacturer and should be read prior to commencement of any rendering.

SUPPLIER :

Kilwaughter Chemical Co. Ltd.

9 Starbog Rd, Larne, Co. Antrim, N. Ireland, BT40 2TJ

Tel: 028 2826 0766 Fax: 028 2826 0136

www.K-Rend.co.uk

APPLICATION METHOD

K Rend HP12 Base and K Rend Silicone TC 15 should be applied strictly in accordance with the manufacturer's instructions and specifications and the relevant sections of BS 5262:1991 and BS EN 13914-1:2005. Further guidance is available in the British Board of Agrément, Certificate No. 97/3428 and the National Standards Authority of Ireland (NSAI), Agrément Certificate No. 06/0248.

Mixing

K Rend R7 Acrylic primer, dilute 1 part K Rend R7 Acrylic with 4 parts water prior to use.

K Rend HP12 Base requires approximately 5-6 litres of clean water per 25 kg sack. Consistency in proportions is essential to ensure an even finish. Mix thoroughly; it takes at least 10 minutes to dissolve the powder additives. Once the products have been mixed to the desired consistency additional water should not be added. The products should not be remixed once the material has started to set.

K Rend Primer TC and K Rend Silicone TC 15; stir the contents of the tub thoroughly before use. (At this stage a small amount of water can be added to Silicone TC 15 to achieve the best working consistency).

Application

K Rend R7 Acrylic primer, apply by brush or roller and the K Rend HP12 Base applied whilst the primer is still wet or tacky.

K Rend HP12 Base, apply by hawk and trowel. Rule to line and level, leave with a float finish. Allow to cure for a minimum 14 days. It is important to ensure that the background is fully dry and protected from rain prior to priming.

Thickness: 10 mm.

K Rend Primer TC, apply by brush or roller. Allow to cure for a minimum of 24 hours prior to application of thin coat finish.

K Rend Silicone TC 15, apply by hand in a continuous application, always working to a wet edge. Apply to the thickness of the largest aggregate. If possible, entire sections or elevations should be coated in a single operation using the same batch to avoid joint marks in the finish.

Finishing

Finishing

Allow Silicone TC 15 to take up slightly prior to rubbing up in a circular motion (using a plastic float or steel trowel) to create the final texture.

Finish: Fine textured.

Total finished thickness: 12 mm.

OTHER CONSIDERATIONS

Site conditions

K Rend products have a working temperature range of 5°C to 35°C. The product should not be applied in the rain or mist, at temperatures above 35°C or below 5°C or if exposure to frost is likely to occur during curing.

In sunny weather work should commence on the shady side of the building and be continued round following the sun to prevent the render drying out too quickly. In cold weather, if frost is forecast, work should stop in time to allow the material to set sufficiently to prevent frost damage. Curing times will vary accordingly to wind, temperature and humidity.

Cleaning of tools

Clean tools and equipment with water immediately after use. Residue from cementitious products must not enter the drainage system.

Curing

All areas should be protected from rain, mist and cold for at least 48 hours after the application of the product. Care should be taken to protect the completed render from drying out too rapidly due to direct sun or drying wind.

Repairs

Damage to the products should be repaired immediately and carried out in accordance with the relevant section of BS 5262:1991 and BS EN 13914:2005. Advice from the manufacturer should be sought. K Rend Silicone TC 15, in common with all finishes, should be protected from all potential site damage.

Algae

The product contains an algae resistant additive which gives enhanced resistance to algae growth. However local conditions may still allow algae growth on the render surface. An annual coat of fungicidal wash can prevent algae from growing on facades which can be prone to algae by remaining wet over prolonged periods.

Water Runs

The product may be subject to water runs, however this may be reduced by proper protection during curing and avoiding application in adverse weather conditions. To avoid the appearance of water runs do not render in cold, damp weather.

Do not permit down-pipes, sills, copings and scaffold boards to throw water on the setting render. Do not allow washings from quoins, sills etc. to run on to the setting render.

Maintenance

Regular maintenance checks should be carried out. Where general staining occurs a warm power wash with suitable detergent can be used to clean up the finish. Care must be taken to adjust the pressure of the power washer to ensure that the render surface is not damaged during the procedure.

This specification is valid for 6 months from date of issue. Thereafter details should be verified with Kilwaughter Chemical Co. Ltd. (Version 10/14)

All Specifications are developed and owned by Kilwaughter Chemical Co. Ltd. for use as internal / external wall coverings. Kilwaughter Chemical Co. Ltd. uses the Specifications in conjunction with its other standard form documents and technical data sheets and in compliance with professional bodies such as RIBA. Kilwaughter Chemical Co. Ltd. does not use the Specifications for any other purpose and does not consider them suitable for use for any other purpose. Electronic copies of specifications in MS Word format are not to be supplied outside the company. Kilwaughter Chemical Co. Ltd. does not permit the possession or use of electronic copies of specifications or guides to specifications by non Kilwaughter Chemical Co. Ltd. organisations or persons other than as stated above.

In line with our policy of continuous improvement, we reserve the right to change technical data without notice.



Certificate No:
FM85394



BSEN998-1 & BSEN-2
Licence No.514639



Certificate No: 06/0248



Kilwaughter Chemical Co Ltd

For UK Sales

9 Starbog Rd, Larne, N. Ireland, BT40 2TJ
Tel: 028 2826 0766 Fax: 028 2826 0136
Email: Sales@K-Rend.co.uk
www.K-Rend.co.uk

For ROI Sales

Classis, Ovens, Co. Cork, Ireland
Tel: 021 4872733 Fax: 021 4871705
Email: Sales@K-Rend.co.uk
www.K-rend.co.uk